

UV PROTECTION
Zinc Oxide Neutral
104702



Zinc Oxide Neutral No. 104702 Microfine Pigment for Effective UVA and UVB Protection

BENEFITS

- Zinc Oxide Neutral is a pigment of fine particle size
- It is nearly transparent to visible light
- No unacceptable whitening of the skin, even when used in high concentrations or after repeated application of cosmetic products containing Zinc Oxide Neutral
- Due to a special manufacturing process Zinc Oxide Neutral is pH neutral and does not shift the pH of cosmetic preparations into the alkaline range
- Zinc Oxide Neutral protects against UV-B and UV-A radiation up to wavelengths of 380 nm
- Easily dispersible in the oil and water phase of emulsions
- Zinc Oxide Neutral has an extremely low content of trace metals, e.g. Pb and As
- Approved to be used up to 25% in the USA, provisionally permitted in Europe
- USP conform

PRODUCT DESCRIPTION

European Patent: 0603627
US Patent: 5527519
CAS No.: 1314-13-2
EINECS: 215-222-5
Molecular Weight: 81.4 g/mol
INCI name: Zinc Oxide



GENERAL DESCRIPTION

Appearance / Condition at 20°C:	white to yellowish powder
Odor:	practically odorless
Pharmacopoeia:	conforms to USP
Primary particle size (nm): (interactive measuring with image analyzing system)	on average 41
Particle size of agglomerates (µm): (Malvern Mastersizer)	on average 2 90% < 5
Specific Surface Area (BET, m ² /g):	30 - 70


ANALYTICAL DATA

ZnO Assay %:	min. 95.0
MgO Assay %:	max. 0.7
SO ₄ ²⁻ Assay %:	max. 2.0
Loss on ignition %:	max. 2.0
pH-value (DIN ISO 787, part 9):	max. 7.5
Shelf life and storage conditions:	36 months in the original, closed container (protected from sunlight), dry, at 5 – 25°C.


IMPORTANT ADVICES FOR FORMULATIONS

- Processing with Zinc Oxide Neutral is simple. It is easily dispersible in the oil and water phases of emulsions. A high energy mixer or, e.g. colloid mill is recommended
- The use of Carbomers to thicken Zinc Oxide containing emulsions is not recommended due to formation of Zinc Acrylates which reduce the gelling properties of Carbomers
- With thickening agents such as Bentone Gel, Veegum, Cellulose types, Xanthan Gum and its derivatives very stable emulsions can be formulated
- The combination of Neo Heliopan® 357 and Zinc Oxide can interact to form a complex which may precipitate out of finished products
- Zinc Oxide and Titanium Dioxide together in a formulation will coalesce resulting in agglomeration if the pH is between the Isoelectric Points of both materials

ZINK OXIDE NEUTRAL
PARTICLE SIZE DISTRIBUTION (VOLUME DISTRIBUTION)



IN-VIVO SPF-DETERMINATION AFTER 27 MONTHS STORAGE



Conclusion:
When manufactured effectively microfine zinc oxide does not agglomerate and does not lose performance with time.

In-Vivo SPF ■ Sept. '93 ■ Dec. '95 ■ Dec. '95 (Fresh)

PATENT SITUATION

We kindly request that attention is paid to the following patents:
EP0585239 B, US5587148 and patent application JP T206-509321.
When contemplating the use of Zinc Oxide Neutral in combination with other UV absorbers, existing patents or patent applications should be considered.

www.symrise.com
scentandcare@symrise.com

DISCLAIMER

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. Symrise makes no warranties, either expressed or implied, as to the accuracy or appropriateness of this data. Symrise expressly disclaims any implied warranty of fitness for a particular use.

We recommend that prospective users determine for themselves the suitability of Symrise materials and suggestions for any use prior to their adoption. We also recommend that prospective users, as required, obtain approval from appropriate regulatory authorities. Suggestions for uses of our products or the inclusion of descriptive material from patents and the citation of specific patents in this publication should not be understood as recommending the use of our products in violation of any patent or as a permission or licence to use any patent of Symrise.